Technical data sheet

PERMACOL® SilGrip 529 with Catalyst SRC18



DESCRIPTION

The PERMACOL SilGrip 529 is a 2 component silicone adhesive with Catalyst SRC18. This adhesive can be used so bond materials such as steel, copper, aluminium, stainless steel, teflon, polyethylene, polypropylene and polyester. This casting resin cures at room temperature, so full cure takes place at 20°C.

Technical details	
Mixing ratio	A:B = 100:3.3 (weight)
Viscosity mixture	1-5 Pa.s (D=30/s 23°C)
Solid content	54-58%
Density	1 g/cm ³
Flash point	2°C
Application temperature	+15°C
Drying time	10 min at 20°C
Pot life	24 hrs at 20°C
Curing time	2-3 days at 20°C
Temperature resistance	-70°C up to +260°C
Usage	2-2.5 m ² /L

USAGE INSTRUCTIONS

Make sure the substrates are clean and free from dust, water, grease, fingerprints, oil, etc. Metals are to be sanded to remove the oxide layer before cleaning. Weigh the components according to the mixing ratio and mix until a homogeneous colour is reached.

If mixing under reduced pressure is applied, keep in mind that the solvent is evaporated as well and can influence the pot life.

BENEFITS

- Quick dry time
- Adhesion to teflon, polyethylene and polypropylene
- Moisture and temperature resistant

CLEANING

Uncured adhesive can be removed and cleaned by means of solvents as Ethanol, Acetone, Isopropanol (IPA) or MEK. Cured adhesives must be removed mechanically.

STORAGE

Store in its original packaging frost free and dry. See packaging for the expiration date. See packaging for expiration date. Shelf life: 6 months.

SAFETY

Use protective gloves to avoid direct contact with the skin. Check the Material Safety Data Sheet for specific safety information.

PACKAGING

The PERMACOL SilGrip 529 with Catalyst SRC18 is available in different kinds of cartridges.

Legal Disclaimer

The products of Permacol (the "Supplier"), are sold subject to the supplier's standard conditions of sale, which are included in applicable sales agreements, printed on the back side of invoices, or available upon request. Although the information, recommendations or advice contained herein is given in good faith, supplier makes no warranty or guarantee, express or implied, (I) that the results described herein will be obtained under end-use conditions, or (II) as to the effectiveness or safety of any design incorporating supplier's products, recommendations or advice. Nothing in this or any other document shall alter, vary, supersede or operate as a waiver of any of the supplier's standard conditions of sale.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's products, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any product is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier, or as a recommendation for the use of such material in the infringement of any patent or other intellectual property right.