

DESCRIPTION

The PERMACOL 5277 UV A/B is a flame retardant polyurethane casting resin which can be applied for example: electrical and mechanical components.

The casting resin cures at room temperature, so full cure takes place at 20°C.

Technical details	
Mixing ratio	A : B = 100 : 20 (weight)
Viscosity	3.000 mPa.s (D=30/s 23°C)
Pot life	90 min at 20°C
Curing time	24 hrs at 20°C
Colour mixture	Grey
Density	1.50 g/cm ³
Hardness	60 shore D
Volume resistance	7×10 ¹² Ω.cm
Dielectric strength	22 KV/mm
Heat conductivity	0.6 W/mK
Permittivity	5.0 at 50Hz
Dissipation factor	0.03 at 50Hz
Temperature resistance	-30°C up to +100°C

USAGE INSTRUCTIONS

Make sure the substrates are clean and free from dust, water, grease, fingerprints, oil, etc. Metals are to be sanded before cleaning.

The A-component should be stirred without producing air bubbles, before adding the B-component.

Weigh the components according to the mixing ratio and mix until a homogeneous colour is reached.

BENEFITS

- Very low shrinkage
- Solvent free
- Flame retardant according to UL94 VO

CLEANING

Uncured adhesive can be removed and cleaned by means of solvents as Ethanol, Acetone, Isopropanol (IPA) or MEK. Cured adhesives must be removed mechanically.

STORAGE

Store in its original packaging frost free and dry, preferably between 15°C and 20°C. This product is sensitive to frost. See packaging for the expiration date. Shelf life: 6 months.

SAFETY

Use protective gloves to avoid direct contact with the skin. Check the Material Safety Data Sheet for specific safety information.

As from 24 August 2023 adequate training is required before industrial or professional use.

PACKAGING

The Permacol 5277 UV A/B is available in different kinds of cans.

Legal Disclaimer

The products of Permacol (the "Supplier"), are sold subject to the supplier's standard conditions of sale, which are included in applicable sales agreements, printed on the back side of invoices, or available upon request. Although the information, recommendations or advice contained herein is given in good faith, supplier makes no warranty or guarantee, express or implied, (I) that the results described herein will be obtained under end-use conditions, or (II) as to the effectiveness or safety of any design incorporating supplier's products, recommendations or advice. Nothing in this or any other document shall alter, vary, supersede or operate as a waiver of any of the supplier's standard conditions of sale.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's products, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any product is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier, or as a recommendation for the use of such material in the infringement of any patent or other intellectual property right.