

## DESCRIPTION

The PERMACOL 2252 A/B is a pasty curing 2-component adhesive. This product is gap filling. This adhesive was developed for roof tiles repair and can also be used bonding: stone, metals, wood, glass and different types of plastics.

The adhesive cures at room temperature, so full cure takes place at 20°C. The curing time will increase at temperatures below 20°C and decrease with temperatures above 20°C.

Technical details	
Mixing ratio	A : B = 100 : 50 (volume)
Pot life	45 min at 20°C
Cure time	24 hrs at 20°C
Viscosity A-component	100 Pa.s at 23°C
Viscosity B-component	15 Pa.s at 23°C
Viscosity mixture	62 Pa.s at 23°C
Colour	Orange or Black
Hardness	84 Shore D
Temperature resistance	-30°C up to +120°C

## USAGE INSTRUCTIONS

Make sure the substrates are clean and free from dust, water, grease, fingerprints, oil, etc. Use the double syringe with a dispensing gun. Place the cartridge into a dispenser gun. Remove the cap from the syringe. Dispense a small amount from the syringe until adhesive is flowing from both sides of the cartridge (do not use this for adhesion). Connect the mixer. Dispense and discard the first mL of adhesive. Begin applying adhesive to the substrate. Do not use these adhesives at temperatures below 5°C.

## BENEFITS

- Room temperature cure
- Gap filling
- Paste-like
- Water removable

## CLEANING

Uncured adhesive can be removed and cleaned by means of water and sponge. Cured adhesives must be removed mechanically.

## STORAGE

Store in its original packaging frost free and dry. See packaging for the expiration date. Shelf life: 12 months.

## SAFETY

Use protective gloves to avoid direct contact with the skin. Check the Material Safety Data Sheet for specific safety information.

## PACKAGING

The PERMACOL 2252 A/B is available in different kinds of cartridges.

## Legal Disclaimer

The products of Permacol (the "Supplier"), are sold subject to the supplier's standard conditions of sale, which are included in applicable sales agreements, printed on the back side of invoices, or available upon request. Although the information, recommendations or advice contained herein is given in good faith, supplier makes no warranty or guarantee, express or implied, (I) that the results described herein will be obtained under end-use conditions, or (II) as to the effectiveness or safety of any design incorporating supplier's products, recommendations or advice. Nothing in this or any other document shall alter, vary, supersede or operate as a waiver of any of the supplier's standard conditions of sale.

*Each user bears the full responsibility for making its own determination as to the suitability of Supplier's products, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any product is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier, or as a recommendation for the use of such material in the infringement of any patent or other intellectual property right.*