

DESCRIPTION

The PERMACOL 2253 A/B is a filled epoxy adhesive with a robust appearance.

This adhesive was developed for stone window sills and can also be used bonding different stone types.

The curing time depends on volume. Larger volumes cure faster.

Technical details	
Mixing ratio	100 : 33,5 (weight)
Viscosity	Thixotropic
Density	1,7 g/ml
Processing temperature	Between 10°C and 35°C
Pot life	90 min at 20°C
Cure time	24 min at 20°C
Curing completed after	48 hrs at 20°C
Colour	Anthracite
Hardness	85 Shore D
Temperature resistance	-30°C up to +120°C

USAGE INSTRUCTIONS

Make sure the substrates are clean and free from dust, water, grease, fingerprints, oil, etc.

Weight both components according to the mixing ratio and mix until a homogeneous mixture is reached.

After applying the adhesive, excess material can be removed and cleaned with a sponge and water.

BENEFITS

- Gap filling
- Robust appearance
- Water removable

CLEANING

Uncured adhesive can be removed and cleaned by means of water and sponge. Cured adhesives must be removed mechanically.

STORAGE

Store in its original packaging frost free and dry, between 5°C and 30°C. See packaging for the expiration date. Shelf life: 12 months.

SAFETY

Use protective gloves to avoid direct contact with the skin. Check the Material Safety Data Sheet for specific safety information.

PACKAGING

The PERMACOL 2253 A/B is available in different kinds of cartridges.

Legal Disclaimer

The products of Permacol (the "Supplier"), are sold subject to the supplier's standard conditions of sale, which are included in applicable sales agreements, printed on the back side of invoices, or available upon request. Although the information, recommendations or advice contained herein is given in good faith, supplier makes no warranty or guarantee, express or implied, (I) that the results described herein will be obtained under end-use conditions, or (II) as to the effectiveness or safety of any design incorporating supplier's products, recommendations or advice. Nothing in this or any other document shall alter, vary, supersede or operate as a waiver of any of the supplier's standard conditions of sale.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's products, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any product is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier, or as a recommendation for the use of such material in the infringement of any patent or other intellectual property right.