

DESCRIPTION

The PERMACOL 5196 A/B series are universal polyurethane adhesives which can be applied for bonding, repair and filling materials like: metals, plastics, mineral substrates, wood and fire resistant building boards.

These adhesives cure at room temperature, so full cure takes place at 20°C.

BENEFITS

- Suitable for outside applications
- Very low shrinkage
- Solvent free
- Resistant to temperature fluxes
- Resistant to oil, grease and acids
- RoHS und REACH compatible

Type	Pot life (at 23°C)	Curing time (at 23°C)	Final strength after(at 23°C)
5196-5	ca. 5 min	ca. 30 min	ca. 24 uur
5196-7	ca. 7 min	ca. 45 min	ca. 24 uur
5196-30	ca. 20 min	ca. 60 min	ca. 24 uur
5196-60	ca. 60 min	ca. 180 min	ca. 24 uur

Technical details	
Mixing ratio	A : B = 1 : 1 (weight, volume)
Viscosity A-component	11.000 mPa.s (D=30/s 23°C)
Viscosity B-component	7.000 mPa.s (D=30/s 23°C)
Minimum application temperature	15°C
Colour mixture	Slight yellow
Hardness	70 shore D
Temperature resistance	-30°C up to +100°C
Shear Strengths	
Steel – Steel	72 kg/cm ²
Aluminium – Aluminium	68 kg/cm ²
Hard PVC – Hard PVC	80 kg/cm ² *
ABS – ABS	45 kg/cm ² *
PMMA – PMMA	82 kg/cm ²
* means material breakage	

USAGE INSTRUCTIONS

Make sure the substrates are clean and free from dust, water, grease, fingerprints, oil, etc. Weigh the components according to the mixing ratio and mix until a homogeneous colour is reached, or use a double syringe and static mixer.

Place the cartridge into a dispenser gun. Remove the cap from the syringe. Dispense a small amount from the syringe until adhesive is flowing from both sides of the cartridge (do not use this for adhesion).

Connect the mixer. Dispense and discard the first mL of adhesive. Begin applying adhesive to the substrate. Do not use these adhesives at temperatures below 5°C.

CLEANING

Uncured adhesive can be removed and cleaned by means of solvents as Ethanol, Acetone, Isopropanol (IPA) or MEK. Cured adhesives must be removed mechanically.

STORAGE

Store in its original packaging frost free and dry. See packaging for the expiration date. Shelf life: 12 months.

SAFETY

Use protective gloves to avoid direct contact with the skin. Check the Material Safety Data Sheet for specific safety information.

As from 24 August 2023 adequate training is required before industrial or professional use.

PACKAGING

The PERMACOL 5196 series are available in different kinds of cartridges.

Legal Disclaimer

The products of Permacol (the "Supplier"), are sold subject to the supplier's standard conditions of sale, which are included in applicable sales agreements, printed on the back side of invoices, or available upon request. Although the information, recommendations or advice contained herein is given in good faith, supplier makes no warranty or guarantee, express or implied, (I) that the results described herein will be obtained under end-use conditions, or (II) as to the effectiveness or safety of any design incorporating supplier's products, recommendations or advice. Nothing in this or any other document shall alter, vary, supersede or operate as a waiver of any of the supplier's standard conditions of sale.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's products, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any product is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier, or as a recommendation for the use of such material in the infringement of any patent or other intellectual property right.