

DESCRIPTION

The PERMACOL 2510 A/B is a 2-component filled adhesive on epoxy basis, which is thermal conductive. This adhesive cures at relative low temperature and bonds good to different materials. After curing the adhesive is stable and obtains good resistance to moisture and heat.

Technical details	
Basis	Epoxy
Colour	Grey
Viscosity A-component	22 Pa.s (D=30/s 23°C)
Viscosity B-component	170 Pa.s (D=30/s 23°C)
Mixing ratio	100 : 100 by weight
Pot life	5-10 min at 23°C
Curing time	3 hrs at 23°C
Final strength after	24 hrs at 23°C
Density	2.11 g/cm ³
Hardness	70 shore D
Volume resistance	> 1 × 10 ¹⁴ Ω.cm
Thermal conductivity coefficient	> 1 W/m.K
Temperature resistance	-30°C up to 140°C

USAGE INSTRUCTIONS

Make sure the substrates are clean and free from dust, water, grease, fingerprints, oil, etc. Weigh the components according to the mixing ratio and mix until a homogeneous colour is reached, or use a double syringe and mix the components until a homogeneous colour is reached.

BENEFITS

- Thermal conductive
- Electrical insulating
- Curing at roomtemperaure
- Little shrinkage
- RoHS und REACH compatible

CLEANING

Uncured adhesive can be removed and cleaned by means of solvents as Ethanol, Acetone, Isopropanol (IPA) or MEK. Cured adhesives must be removed mechanically.

STORAGE

Store in its original packaging frost free and dry, between 10°C and 25°C. See packaging for the expiration date. Shelf life: 6 months.

SAFETY

Use protective gloves to avoid direct contact with the skin. Check the Material Safety Data Sheet for specific safety information.

PACKAGING

The PERMACOL 2510 A/B is available in different kinds of cartridges, cans and jars.

Legal Disclaimer

The products of Permacol (the "Supplier"), are sold subject to the supplier's standard conditions of sale, which are included in applicable sales agreements, printed on the back side of invoices, or available upon request. Although the information, recommendations or advice contained herein is given in good faith, supplier makes no warranty or guarantee, express or implied, (I) that the results described herein will be obtained under end-use conditions, or (II) as to the effectiveness or safety of any design incorporating supplier's products, recommendations or advice. Nothing in this or any other document shall alter, vary, supersede or operate as a waiver of any of the supplier's standard conditions of sale.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's products, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any product is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier, or as a recommendation for the use of such material in the infringement of any patent or other intellectual property right.