

DESCRIPTION

The PERMACOL 2177 A/B is a 2-component epoxy casting resin. This product is a tough elastic, which gives it the property to absorb a difference in expansion. A few of the applications in which this adhesive is used are casting electrical connections and components, as protective layer on plastics or as dip material.

This adhesive cures at room temperature, so full cure takes place at 20°C. The curing time will increase at temperatures below 20°C.

Technical details	
Mixing ratio	A : B = 100 : 15 (weight)
Pot life	2 hrs at 20°C
Cure time	ca. 24 hrs at 20°C
Final strength after	ca. 24 hrs at 20°C
Viscosity mixture	1.400 mPa.s at 23°C
Colour	Black
Temperature resistance	-30°C up to +130°C
Hardness	45 shore D

USAGE INSTRUCTIONS

Make sure the substrates are clean and free from dust, water, grease, fingerprints, oil, etc. Weight the components and mix in advised mixing ratio. Stir steady and equable until a homogenous product arises. Perhaps under reduced pressure to avoid air bubbles.

Legal Disclaimer

The products of Permacol (the "Supplier"), are sold subject to the supplier's standard conditions of sale, which are included in applicable sales agreements, printed on the back side of invoices, or available upon request. Although the information, recommendations or advice contained herein is given in good faith, supplier makes no warranty or guarantee, express or implied, (I) that the results described herein will be obtained under end-use conditions, or (II) as to the effectiveness or safety of any design incorporating supplier's products, recommendations or advice. Nothing in this or any other document shall alter, vary, supersede or operate as a waiver of any of the supplier's standard conditions of sale.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's products, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any product is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier, or as a recommendation for the use of such material in the infringement of any patent or other intellectual property right.

BENEFITS

- Tough elastic
- Good resistance to water, thin acids, bases and oil
- Suitable for casting electronics
- Good temperature resistance
- Gap filling
- RoHS and REACH compliant

CLEANING

Uncured adhesive can be removed and cleaned by means of solvents as Ethanol, Acetone, Isopropanol (IPA) or MEK. Cured adhesives must be removed mechanically.

STORAGE

Store in its original packaging frost free and dry. See packaging for the expiration date. Shelf life: 12 months.

SAFETY

Use protective gloves to avoid direct contact with the skin. Check the Material Safety Data Sheet for specific safety information.

PACKAGING

The PERMACOL 2177 A/B is available in different kinds of sizes