

Technical data sheet

PERMACOL 3510-series



DESCRIPTION

The PERMACOL 3510 series are optically clear UV-curing adhesives especially designed for bonding PMMA (acrylic glass / perspex / plexiglass). The monomer of this adhesive is methyl-methacrylate (MMA). During curing PMMA is formed. So by using this adhesive PMMA is bonded with PMMA. This results in a very strong bond.

Technical details	
Chemical type	Methyl-methacrylate
Components	One component
Color	Clear
Viscosity 3510-1	70 mPas
Viscosity 3510-2	750 mPas
Specific gravity	0,95 g/cm ³
UV-wavelength	320 – 400nm

USAGE INSTRUCTIONS

Can be cured with low intensity UV-A lamps. Curing time depends on the spectrum and intensity of the lamp and the layer-thickness of the adhesive. Curing time for a thin layer with a low intensity UV-A light or direct sunlight is about 5-10 minutes for the 3510-1 and 3-8 minutes for the 3510-2.

Maximum bonding strength is reached a couple of hours after curing. Higher intensity UV-lamps will speed up the curing process. Curing with UV-LED lamps is not recommended.

EN – Legal Disclaimer

The products of Permacol (the "Supplier"), are sold subject to the supplier's standard conditions of sale, which are included in applicable sales agreements, printed on the back side of invoices, or available upon request. Although the information, recommendations or advice contained herein is given in good faith, supplier makes no warranty or guarantee, express or implied, (I) that the results described herein will be obtained under end-use conditions, or (II) as to the effectiveness or safety of any design incorporating supplier's products, recommendations or advice. Nothing in this or any other document shall alter, vary, supersede or operate as a waiver of any of the supplier's standard conditions of sale.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's products, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any product is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier, or as a recommendation for the use of such material in the infringement of any patent or other intellectual property right.

Make sure the substrates are clean and free from dust, water, grease, fingerprints, oil, ect. Use isopropanol to clean the substrates.

BENEFITS

- Bonds PMMA GS and XT
- Optically clear
- Capillary (3510-1), gap-filling (3510-2)
- 100% solids, no solvents
- Curable with low intensity UV-light
- RoHS and REACH compliant

STORAGE

Store in its original packaging below 20°C. Allow the adhesive to warm up to room temperature before use. This product is light sensitive. Avoid direct exposure to daylight and artificial lighting. See packaging for the expiration date. Shelf life: 12 months.

SAFETY

Use protective gloves to avoid direct contact with the skin. Keep away from fire. Check the Material Safety Data Sheet for specific safety information.

PACKAGING

The PERMACOL 3510 series are available in different kinds of cartridges and bottles