

DESCRIPTION

The PERMACOL 2163 A/B is a 2-component epoxy casting resin, which is transparent with light yellow.

Applications in which this adhesive is used are casting electrical connections and components, as protective layer on plastics or as dip material.

This adhesive cures at room temperature, so full cure takes place at 20°C. The curing time will increase at temperatures below 20°C. The curing time will decrease for larger mass.

BENEFITS

- Low viscosity
- Transparent
- Good resistance to water, thin acids, bases and oil
- Suitable for casting electronics
- Good temperature resistance
- Gap filling
- RoHS and REACH compliant

Technical details	
Mixing ratio	A : B = 100 : 50 (weight/volume)
Pot life	ca. 30 min (100gr at 20°C)
Cure time	ca. 1.5 hrs at 20°C
Final strength after	ca. 24 hrs at 20°C
Viscosity mixture	400 mPa.s at 23°C
Colour	Transparent light yellow
Hardness	80 shore D

CLEANING

Uncured adhesive can be removed and cleaned by means of solvents as Ethanol, Acetone, Isopropanol (IPA) or MEK. Cured adhesives must be removed mechanically.

STORAGE

Store in its original packaging frost free and dry. See packaging for the expiration date. Shelf life: 12 months.

USAGE INSTRUCTIONS

Make sure the substrates are clean and free from dust, water, grease, fingerprints, oil, etc. Metals are to be sanded to remove the oxide layer before cleaning. Weigh the components according to the mixing ratio and mix until a homogeneous colour is reached. The pot life is depending on the volume that is mixed. Larger volumes have a shorter pot life and reach a higher exothermal temperature.

SAFETY

Use protective gloves to avoid direct contact with the skin. Check the Material Safety Data Sheet for specific safety information.

PACKAGING

The PERMACOL 2163 A/B is available in different kinds of sizes

Legal Disclaimer

The products of Permacol (the "Supplier"), are sold subject to the supplier's standard conditions of sale, which are included in applicable sales agreements, printed on the back side of invoices, or available upon request. Although the information, recommendations or advice contained herein is given in good faith, supplier makes no warranty or guarantee, express or implied, (I) that the results described herein will be obtained under end-use conditions, or (II) as to the effectiveness or safety of any design incorporating supplier's products, recommendations or advice. Nothing in this or any other document shall alter, vary, supersede or operate as a waiver of any of the supplier's standard conditions of sale.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's products, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any product is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier, or as a recommendation for the use of such material in the infringement of any patent or other intellectual property right.